



MONDIALCARTA S.p.A

SPECIFICHE TECNICHE

TEST LINER 3 SIZED

All items are 100% FSC Recycled

Data validità	01/01/2024
fino al	31/12/2024

proprietà	unità di misura	norma di riferimento	Valori					
-----------	-----------------------	----------------------------	--------	--	--	--	--	--

Grammatura nominale	g/m ²		105	120	130	150	160	180
---------------------	------------------	--	------------	------------	------------	------------	------------	------------

Grammatura	g/m ²	UNI EN ISO 536:2012	min	103	118	128	148	158	177
			max	108	122	132	152	162	183

Umidità	%	UNI EN ISO 287:2009	min	6,00	6,00	6,00	6,00	6,00	6,00
			max	8,00	8,00	8,00	8,00	8,00	8,00

Cobb-60" (copertina)	g/m ²	UNI EN ISO 535:2014	min	35	35	35	35	35	35
			max	23	23	23	23	23	23

Cobb-60" (retro)	g/m ²	UNI EN ISO 535:2014	min	70	70	70	70	70	70
			max	50	50	50	50	50	50

Indice di scoppio	kPa.m ² /g	UNI EN ISO 2758:2004	min	2,14	2,03	2,00	1,85	1,90	1,80
			max	2,22	2,30	2,20	2,15	2,10	2,00

Resistenza alla compressione su anello (RCT)	kN/m	ISO 12192:2011	min	0,70	0,90	1,00	1,30	1,40	1,85
			max	0,90	1,15	1,30	1,50	1,60	2,00

Resistenza alla compressione direzione macchina (SCT)	kN/m	UNI ISO 9895:2009	min	2,40	2,80	3,30	3,50	4,20	4,50
			max	2,80	3,10	3,80	4,40	4,60	5,00

Resistenza alla compressione direzione trasversale (SCT)	kN/m	UNI ISO 9895:2009	min	1,40	1,60	1,80	1,90	2,30	2,50
			max	1,70	1,90	2,10	2,40	2,50	3,00