



MONDIALCARTA S.p.A

SPECIFICHE TECNICHE

TEST LINER 3

All items are 100% FSC Recycled

Data validità	01/01/2023
fino al	31/12/2023

proprietà	unità di misura	norma di riferimento		Valori					
Grammatura nominale	g/m ²			105	120	130	150	160	180
Grammatura	g/m ²	UNI EN ISO 536:2012	min	103	118	128	148	158	177
			max	108	122	132	152	162	183
Umidità	%	UNI EN ISO 287:2009	min	6,00	6,00	6,00	6,00	6,00	6,00
			max	8,00	8,00	8,00	8,00	8,00	8,00
Resistenza allo scoppio	kPa	UNI EN ISO 2758:2004	min	220	240	256	274	300	319
			max	240	280	290	327	340	366
Indice di scoppio	kPa.m ² /g	UNI EN ISO 2758:2004	min	2,14	2,03	2,00	1,85	1,90	1,80
			max	2,22	2,30	2,20	2,15	2,10	2,00
Resistenza alla compressione su anello (RCT)	kN/m	ISO 12192:2011	min	0,70	0,90	1,00	1,30	1,40	1,85
			max	0,90	1,15	1,30	1,50	1,60	2,00
Resistenza alla compressione direzione macchina (SCT)	kN/m	UNI ISO 9895:2009	min	2,40	2,80	3,30	3,50	4,20	4,50
			max	2,80	3,10	3,80	4,40	4,60	5,00
Resistenza alla compressione direzione trasversale (SCT)	kN/m	UNI ISO 9895:2009	min	1,40	1,60	1,80	1,90	2,30	2,50
			max	1,70	1,90	2,10	2,40	2,50	3,00

MONDIALCARTA SPA